



SMT SOLUTIONS INC  
160 JOHNSON AVE  
HACKENSACK, NJ 07601 USA  
ATTN: LARRY EDINGER

December 5, 2007

**IDENTIFICATION SUBMITTED BY CLIENT**

SAMPLE DESCRIPTION : DISPOSABLE TABLE SKIRT  
STYLE NO. : JF 6003-30  
COLOR (S) : GREY  
PO NO : 60

**FIRE RESISTANCE - STATE OF CALIFORNIA (NATURALS/SYNTHETICS)**

Synthetics Title 19 Chapter 8 Section 1263.9 for FR chemicals applied to  
Std. Synthetic Interior test fabrics

**EVALUATION OF TEST RESULTS**

The fabric sample submitted **DOES** meet the requirements when tested, in accordance with procedure outlined in Specifications for Flame-Retardant Chemicals, Fabrics and Application concerns, California Administrative Code Title 19 (Interior Use).

	<b>AFTERFLAME (Seconds)</b>	<b>CHAR LENGTH (Inches)</b>
1 Warp/length	0.0	5.8
2 Warp/length	0.0	5.4
3 Warp/length	0.0	4.4
4 Filling/width	0.0	4.5
5 Filling/width	0.0	4.5
6 Filling/width	0.0	<u>4.5</u>
<b>Average:</b>		4.9

Afterglow: NO                      **OBSERVATIONS**  
Localized Burning                      NO

**FIRE RESISTANCE REQUIREMENTS: NATURALS AS PER SECTION 1261**

Afterflame shall not exceed 1.0 second for any one specimen  
Average char length shall not exceed 3.5 inches.  
Char Length shall not exceed 6.0 inches for any one specimen.

**FIRE RESISTANCE REQUIREMENTS: SYNTHETICS AS PER SECTION 1263.9**

Afterflame shall not exceed 1.0 second for any one specimen  
Average char length shall not exceed 6 inches.



Report Number: **138322**

**IF YOU NEED ASSISTANCE IN INTERPRETING THESE TESTS RESULTS  
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:  
CUSTOMER SERVICE DEPT.**

**INTERTEK LABTEST**

A handwritten signature in blue ink that reads "Eduardo Palomo". The signature is fluid and cursive, with a long horizontal stroke extending to the right.

Eduardo Palomo  
Senior Client Manager

**AZ**