



SMT SOLUTIONS
52 1ST STREET
HACKENSACK, NJ 07601
ATTN: ALBERTO LOPEZ
EMAIL: alberto@smtsolutions.com

MAY 12, 2011

IDENTIFICATION SUBMITTED BY CLIENT

DESCRIPTION : DISPOSABLE TABLE SKIRT
STYLE # : 6001-30
PO# : 138
COLORS : BLACK





TEST RESULTS

FIRE RESISTANCE - STATE OF CALIFORNIA (NATURALS/SYNTHETICS)

- Naturals Title 19 Chapter 8 Section 1261 for FR chemicals applied to Std. Cotton Interior test fabrics
- X Synthetics Title 19 Chapter 8 Section 1263.9 for FR chemicals applied to Std. Synthetic Interior test fabrics

EVALUATION OF TEST RESULTS

The fabric sample submitted **DOES** meet the requirements when tested, in accordance with procedure outlined in Specifications for Flame-Retardant Chemicals, Fabrics and Application concerns, California Administrative Code Title 19 (Interior Use).

Test Results			
		AFTERFLAME	CHAR LENGTH
Specimen	Direction	(Seconds)	(Inches)
1	LENGTH	0	6.1
2	LENGTH	0	6.0
3	LENGTH	0	5.3
4	WIDTH	0	6.4
5	WIDTH	0	5.6
6	WIDTH	0	5.1
Average:		0	5.8

OBSERVATIONS

Afterglow: YES NO Localized Burning YES NO

FIRE RESISTANCE REQUIREMENTS: NATURALS AS PER SECTION 1261

Afterflame shall not exceed 1.0 second for any one specimen
Average char length shall not exceed 3.5 inches.
Char Length shall not exceed 6.0 inches for any one specimen.

FIRE RESISTANCE REQUIREMENTS: SYNTHETICS AS PER SECTION 1263.9

Afterflame shall not exceed 1.0 second for any one specimen
Average char length shall not exceed 6 inches.



**IF YOU NEED ASSISTANCE IN INTERPRETING THESE TESTS RESULTS
OR IF YOU HAVE ANY QUESTIONS, PLEASE FEEL FREE TO CALL:
CUSTOMER SERVICE DEPARTMENT.**

INTERTEK CONSUMER GOODS

Javier Gaviria
Account Manager
JM

Curtis Jones
Account Manager

Stanley Sherrill
General Manager of
Consumer Goods North America